



BoneDry™ RG

Specification Sheet

2034-C Van Buren Ave. • Indian Trail, NC 28079 • Phone: 704.334.8222

BoneDry™ RG is a commercial grade waterproofing membrane designed to be applied with a roller. **BoneDry™ RG** is used as a below-grade exterior waterproofing compound and exhibits excellent strength, adhesion, and flexibility. **BoneDry™ RG** is a premium grade waterproofing compound used in commercial building construction and can be used for all other types of below-grade waterproofing.

BoneDry™ RG is designed to be applied with a roller. We recommend that the **BoneDry™ RG** be applied to a cured thickness of 40 - 60 mils. It may take several applications to obtain a 40 - 60 mil cured membrane.

Technical Data

Color		Black/Brown
Solids		63% ± 2%
Thickness		40-60 mil dry
Tensile Strength	ASTM D-412	87 psi
Elongation	ASTM D-412	1800%
MVT	ASTM E-96	0.19 gr/hr*sq.ft
Adhesion to Concrete	ASTM C-834	Exceeds
Shore Hardness	ASTM C-836	75
Crack Bridging	ASTM C-836	Exceeds
Low Temp Flexibility	ASTM C-836	No Cracking
Perm Rating	ASTM C-836	0.38 perms

For more application
information visit
www.drydogbarriers.com
or email us
info@drydogbarriers.com

Applications

- Masonry Foundations
- Poured Foundations
- Pre-Cast Foundations
- Horizontal Waterproofing
- Planters
- Retaining Walls
- Cavity Wall Air Barrier

The information and recommendations discussed in this publication are believed to be correct. However, this should not be accepted as a guarantee of their accuracy, and confirming test should be run in your own plant or laboratory. No statement should be construed as a recommendation for any use, which would violate any patent rights. Nothing contained herein shall constitute a warranty with respect to the products described or their use.

BoneDry™RG
Issue: A
Revision: 1
Date: 01/01/07